

# **Laboratory Scale Evaluation of Hydra-Tone Graff-Off™ Coconut Oil-Based Degreaser**

by

James R. Nutor and James K. Rose  
Battelle  
505 King Avenue  
Columbus, Ohio 43201-2693

Contract No. 68-C7-0008  
Work Assignment Numbers 2-19

to  
Dr. George Moore  
Project Officer

and  
Mr. David Ferguson  
Work Assignment Manager

U.S. Environmental Protection Agency  
Office of Research and Development  
National Risk Management Research Laboratory  
Cincinnati, Ohio 45268

---

## **Notice**

The information in this document has been funded by the United States Environmental Protection Agency (U.S. EPA) under Work Assignment (WA) Nos. 2-19 of Contract No. 68-C7-0008 to Batelle. It has been subjected to the U.S. EPA's peer and administrative reviews, and has been approved for publication as a U.S. EPA document. Mention of trade names or commercial products does not constitute an endorsement or recommendation for use.

---

## **Abstract**

This technical and economic assessment evaluated the effectiveness of a biodegradable, coconut oil-based degreaser called Graff-Off™. In immersion (“cold”) cleaning and rinse tests, Graff-Off™ was compared to a conventional chlorinated solvent 1,1,1 trichloroethane (TCA) and to an alkaline cleaner Aeroclean DN-30 (DN-30). The cleaning process for Graff-Off™ and TCA was at room temperature and that of DN-30 was at 71° C. Both alternatives were found to be technically superior to TCA. Both alternative degreasers had lower cleaner costs and allowed a greater surface area to be cleaned per unit volume of degreaser than the TCA. Estimated savings were significant and capital requirements were modest. An economic assessment based on net present value, internal rate of return, and payback period indicated that Graff-Off™ and the DN-30 alkaline cleaner were extremely attractive alternatives to TCA (TCA assessment was based on immersion “cold” cleaning without vaporization and without TCA recycling).

---

---

## Contents

Notice .....	ii
Abstract .....	iii
Contents .....	v
Figures .....	vii
Tables .....	viii
Acronyms and Abbreviations .....	ix
Foreword .....	x
<b>1.0 Introduction .....</b>	<b>1</b>
1.1 Background .....	1
1.2 Industrial Opportunity .....	1
1.3 Objective .....	1
<b>2.0 Conclusions .....</b>	<b>2</b>
<b>3.0 Recommendations .....</b>	<b>3</b>
<b>4.0 Methods and Materials .....</b>	<b>4</b>
4.1 Test System Definition and Selection .....	4
4.1.1 Cleaning Process Selection .....	4
4.1.2 Alternate Alkaline Cleaner Selection .....	4
4.1.3 Solvent Cleaner Selection .....	4
4.1.4 Cleaning Object Selection .....	4
4.1.5 Contaminant Selection .....	4
4.1.6 Pre-Contamination of Degreaser Bath .....	4
4.2 Experimental Set-up .....	4
4.2.1 Materials .....	4
4.2.2 Beaker Test for Bath Exhaustion Determination .....	5
4.2.3 Panel Contamination .....	5
4.2.3.1 Panel Holding Racks .....	5
4.2.3.2 Panel Labeling .....	5
4.2.3.3 Automated Immersion Unit .....	5
4.2.3.4 Panel Contamination Process .....	5
4.3 Cleaning Process .....	5
4.3.1 Cleaning Bath .....	6
4.3.2 Rinse Tanks .....	6
4.3.3 Cleaning System Accessories .....	6
4.3.4 Cleaning Operation .....	7
4.3.4.1 Preparation for Contaminated Panel Cleaning .....	7
4.3.4.2 Panel Cleaning Procedure .....	7
4.3.4.3 Rejuvenation of Exhausted Baths .....	8
4.4 Performance Measurements .....	8
4.4.1 Panel Sampling .....	9
4.4.2 Bath Exhaustion Indicators .....	9
4.4.2.1 Water-Break Test .....	10
4.4.2.2 Weight Change Test .....	10
4.4.2.3 Non-Volatile Residue Measurements (NVR) .....	10
4.4.2.4 Fourier Transform Infrared Spectroscopy (FTIR) .....	10
4.4.3 Rinse Bath Monitoring .....	10
4.4.4 Other Observational Methods .....	10
4.5 Economic Assessment .....	10

---

5.0	Results and Discussion .....	12
5.1	Load of Jet Engine Oil on Contaminated Panels .....	12
5.2	Beaker Test for Predicting Bath Exhaustion Level and Bath Pre-Contamination Level .....	12
5.3	Cleaning Performance by Water-Break Test .....	13
5.4	Alternative Performance Measure Test .....	13
5.5	Cleaning Performance by Other Observations .....	13
5.5.1	Physical Properties of the Cleaners .....	13
5.5.2	Cleaning Process Observations .....	13
5.5.3	pH and Temperature of Baths .....	13
5.5.4	Particulates in the Cleaning Baths .....	14
5.5.5	Panel Corrosion .....	14
5.6	Rejuvenation of Exhausted Degreaser Baths .....	14
6.0	Economic Analysis .....	16
6.1	Assumptions .....	16
6.1.1	Commercial Job Shop .....	16
6.1.2	Large Shop Operation .....	16
6.2	Life Cycle Analysis .....	18
6.2.1	Financial Performance Measure .....	18
6.2.2	Capital Costs .....	18
6.2.3	Retrofit Cost .....	18
6.2.4	Capital Replacement .....	18
6.2.5	Annual Operating Costs .....	20
6.3	Investment Analysis and Conclusions .....	20
7.0	References .....	24
8.0	Appendices .....	25

---

## Figures

Figure 1.	Panel rack. ....	6
Figure 2.	Automated test panel immersion system. ....	7
Figure 3.	Cleaner bath with submerged rack and panels. ....	8
Figure 4.	Rinse tanks with rinse water addition nozzles. ....	9
Figure 5.	Beaker test results compared to actual bath cleaning results. ....	14
Figure 6.	Total surface area cleaned at bath exhaustion. ....	15

---

## Tables

Table 1.	List of Critical and Non-Critical Performance Measurements .....	9
Table 2.	Summary of Non-Critical Surface Finishing Bath and Rinse Water Analyses .....	10
Table 3.	Results of Beaker Test .....	12
Table 4.	Estimated Degreaser Requirements .....	17
Table 5.	Utility Requirements .....	17
Table 6.	Large-Scale Operations Degreaser Requirements .....	18
Table 7.	Large-Scale Operations Utility Requirements .....	19
Table 8.	Estimated Values Used in the Cost Assessment .....	19
Table 9.	Summary of Investment Criteria .....	20
Table 10.	Estimated Initial Capital Investment .....	20
Table 11.	Retrofit and Training Costs .....	21
Table 12.	Estimated Net Change in Capital Investment .....	21
Table 13.	Estimated Annual Costs .....	22
Table 14.	Investment Assessment .....	23



---

## Acronyms and Abbreviations

ASTM	American Society for Testing and Materials
CAA	Clean Air Act
CFC	chlorofluorocarbons
COCF	Chain of Custody Form
DN-30	Aeroclean DN-30 – an alkaline cleaner
EPA	United States Environmental Protection Agency
FTIR	Fourier Transform Infrared Spectroscopy
HBFC	hydrogen bromine fluorocarbons
HCFC	hydrogen chlorofluorocarbons
HTCI	Hydra-tone Chemicals, Inc.
IRR	internal rate of return
NPV	net present value
NRMRL	National Risk Management Research Laboratory
NVR	non-volatile residue
PCE	perchloroethylene
PE	purchased equipment
P2	Pollution Prevention
QC	quality control
TCA	1,1,1 trichloroethane – a solvent cleaner
TCE	trichloroethylene
TO	technical order
U.S. EPA	United States Environmental Protection Agency
VOCs	volatile organic compounds

---

## Foreword

The U.S. Environmental Protection Agency is charged by Congress with protecting the Nation's land, air, and water resources. Under a mandate of national environmental laws, the Agency strives to formulate and implement actions leading to a compatible balance between human activities and the ability of natural systems to support and nurture life. To meet this mandate, EPA's research program is providing data and technical support for solving environmental problems today and building a science knowledge base necessary to manage our ecological resources wisely, understand how pollutants affect our health, and prevent or reduce environmental risks in the future.

The National Risk Management Research Laboratory (NRMRL) is the Agency's center for investigation of technological and management approaches for preventing and reducing risks from pollution that threaten human health and the environment. The focus of the Laboratory's research program is on methods and their cost-effectiveness for prevention and control of pollution to air, land, water, and subsurface resources; protection of water quality in public water systems; remediation of contaminated sites, sediments and ground water; prevention and control of indoor air pollution; and restoration of ecosystems. NRMRL collaborates with both public and private sector partners to foster technologies that reduce the cost of compliance and to anticipate emerging problems. NRMRL's research provides solutions to environmental problems by: developing and promoting technologies that protect and improve the environment; advancing scientific and engineering information to support regulatory and policy decisions; and providing the technical support and information transfer to ensure implementation of environmental regulations and strategies at the national, state, and community levels.

This publication has been produced as part of the Laboratory's strategic long-term research plan. It is published and made available by EPA's Office of Research and Development to assist the user community and to link researchers with their clients.

E. Timothy Oppelt, Director  
National Risk Management Research Laboratory